

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 339 742
A2**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89201064.6

(51) Int. Cl.⁴: C09D 3/48 , C23C 4/04 ,
C08G 67/02 , C08J 5/12

(22) Date of filing: 25.04.89

(30) Priority: 25.04.88 US 185577

(43) Date of publication of application:
02.11.89 Bulletin 89/44

(84) Designated Contracting States:
BE CH DE ES FR GB IT LI NL SE

(71) Applicant: SHELL INTERNATIONALE
RESEARCH MAATSCHAPPIJ B.V.
Carel van Bylandtlaan 30
NL-2596 HR Den Haag(NL)

(72) Inventor: George, Eric Richard
13703 Overbrook Lane
Houston Texas 77077(US)

(74) Representative: Aalbers, Onno et al
P.O. Box 302
NL-2501 CH The Hague(NL)

(54) Process for coating a solid object with a polymeric material.

(57) A coated object is produced by flame spraying the object with a substantially molten polymeric material which comprises a linear alternating polymer of ethylene and at least one ethylenically unsaturated compound, optionally blended with a copolymer of ethylene and alpha,beta-ethylenically unsaturated carboxylic acid.

EP 0 339 742 A2

PROCESS FOR COATING A SOLID OBJECT WITH A POLYMERIC MATERIAL

The invention relates to a process for coating a solid object with a polymeric material by flame spraying.

Flame spraying is a technology mainly used for coating solid articles with a layer of metal, especially zinc or aluminium. Sometimes it is called metal spraying therefore. It comprises a process in which a molten substance, e.g. a metal, is propelled onto a substrate by spraying, for example by using a spray gun. The molten droplets cool and partially solidify during their journey from the spray gun to the substrate, so that they arrive in a viscous, half-solid state, and are flattened on impact. This provides a relatively porous layer on the substrate without creating an alloy therewith. There are three basic techniques:

1. spraying molten material from a melting cup, no longer in common use because of technical difficulties;

2. wire spraying, comprising melting a wire in a gas-oxygen flame, an electrical arc or a plasma torch, followed by spraying using air or another gas; and

3. powder spraying, in which the material is provided in powdery form to the flame, arc or torch and is subsequently sprayed.

In the latter technique the powder may also be supplied in a compressed form, that is as rods, so that the powder may be sprayed as a "wire". A special way of heating and propelling the powder in one combined step consists in the use of shock waves, in a so-called detonation gun.

Though flame spraying is mainly used with metals, it is known to flame spray polymeric materials such as polyethylene, PVC and polyamide too, but, as noted in Winkler Prins Technische Encyclopedie, Volume 5, pages 72-73, Amsterdam (1978), this method is less attractive because surface burning of the polymer particles reduces their quality and because other coating methods, such as sintering in fluidized beds and electrostatic spraying, are convenient and do not deteriorate the material as much. On the other hand, it would be advantageous to dispose of a polymeric material which can be flame sprayed with ease and without significant deterioration, as only the flame spraying method can be used with objects of unlimited size, and permits to apply layers of any thickness, and of variable thickness if desired.


It has now been found, that this object may be achieved by choosing a polyketone polymer powder of a specific viscosity and particle size, which is optionally admixed to a copolymer of ethylene and an alpha,beta-ethylenically unsaturated car-

boxylic acid.

Accordingly, the invention relates to a process for coating a solid object with a polymeric material by flame spraying characterized in that a powder having a particle size of 0.15-0.85 mm comprising a linear alternating polymer of carbon monoxide and at least one ethylenically unsaturated compound, which linear alternating polymer has a limiting viscosity number of 0.5-1.8 (as measured at 60° C in m-cresol), is heated to substantially melt the powder, and is thereafter propelled onto the surface of the solid object.

The polyketone polymer which is employed in the process of the invention is a linear alternating polymer of carbon monoxide and at least one ethylenically unsaturated compound. Suitable ethylenically unsaturated compounds for use as precursors of the polyketone polymers have up to 20 carbon atoms inclusive, preferably up to 10 carbon atoms inclusive, and are aliphatic such as ethylene and other alpha-olefins including propylene, butylene, isobutylene, 1-hexene, 1-octene and 1-dodecene, or are arylaliphatic containing an aryl substituent on a carbon atom of an otherwise aliphatic molecule, particularly an aryl substituent on a carbon atom of the ethylenic unsaturation and may be substituted with functional groups such as carboxyl or acid amide groups. Illustrative of this latter class of ethylenically unsaturated hydrocarbons are styrene, m-methylstyrene, p-ethylstyrene and p-methylstyrene. Preferred polyketones are copolymers of carbon monoxide and ethylene or terpolymers of carbon monoxide, ethylene and a second hydrocarbon of at least 3 carbon atoms, particularly an alpha-olefin such as propylene.

The structure of the polyketone polymers is that of a linear alternating polymer of carbon monoxide and ethylenically unsaturated compound and contains substantially one molecule of carbon monoxide for each molecule of unsaturated compound. When terpolymers of carbon monoxide, ethylene and a second hydrocarbon are employed, there will be within the terpolymer at least two units incorporating a moiety of ethylene for each unit employing a moiety of the second hydrocarbon. Preferably there will be from 10 units to 100 units incorporating a moiety of ethylene per unit employing a molecule of the second hydrocarbon. The polymer chain is therefore illustrated by the formula



wherein B is the moiety of the second hydrocarbon polymerized through the ethylenic unsaturation. The $-\{CO\{CH_2-CH_2\}\}$ units and the $-CO\{B\}$ units are found randomly throughout the polymer chain and the ratio of y:x is no more than 0.5. In the

modification of the invention where copolymer of ethylene and carbon monoxide is employed, the polymer is illustrated by the above formula wherein $y = 0$. When y is other than 0, as in the case of terpolymers, ratios of $y:x$ from 0.1 to 0.01 are preferred. The end groups or "caps" of the polymer chain will depend on what materials are present during the production of the polymer and whether and how the polymer is purified. The precise nature of the end groups is of little significance so far as the overall properties of the polymer are concerned, so that the polyketone polymer is fairly represented by the above formula. Of particular interest are the polymers of molecular weight from 1,000 to 200,000, particularly those polyketone polymers of molecular weight from 10,000 to 50,000. The physical properties of the polymers will depend in part on whether the polymer is a copolymer or a terpolymer and the relative proportion of second hydrocarbon present in the case of terpolymers. Typical melting points of such polymers are from 175°C to 300°C, but more typically from 210°C to 270°C. The polymers have limiting viscosity numbers (measured at 60°C in *m*-cresol) of from 0.5 to 10, more commonly from 0.8 to 4, as measured in a standard capillary viscosity measuring device.

A method of producing the polymers which is now becoming conventional is to contact the carbon monoxide and unsaturated compound(s) in the presence of a catalyst composition formed from a palladium compound, the anion of a non-hydrohalogenic acid having a pK_a below 6 and a bidentate phosphorus ligand of defined structure. The scope of the process of producing the polyketone polymer is extensive, but without wishing to be limited, the preferred palladium compound is a palladium carboxylate, particularly palladium acetate, the preferred anion is the anion of trifluoroacetic acid or *p*-toluenesulphonic acid and the preferred bidentate phosphorus ligand is 1,3-bis(diphenylphosphino)propane or 1,3-bis(di(2-methoxyphenyl)phosphino)propane. Such a process for polyketone production is illustrated by *inter alia* European patent applications 121,965 and 181,014.

The flame spray process of the invention is usefully conducted employing the polyketone polymer without the addition of other materials. However, conventional additives such as pigments, antioxidants and stabilizers which are designed to improve the properties of the coated object may be incorporated within the polyketone polymer. In a particular embodiment, however, the polyketone is blended with a second polymeric component and the resulting blend is employed in the flame coating process. A preferred second polymeric material is a copolymer of ethylene and α,β -

ethylenically unsaturated carboxylic acid. Although a variety of such unsaturated carboxylic acids of up to 10 carbon atoms inclusive, or in some cases even more, is useful as a monomer in the ethylene copolymers, e.g., 2-hexenoic acid, 2-octenoic acid and 2-decenoic acid, the preferred ethylenically unsaturated acids are those of up to 4 carbon atoms inclusive which are acrylic acid, methacrylic acid and crotonic acid. Methacrylic acid and acrylic acid are particularly preferred components of the ethylene/unsaturated carboxylic acid copolymer.

The ethylene/unsaturated carboxylic acid copolymers are those copolymers having a relatively large proportion of ethylene and a relatively small proportion of the unsaturated carboxylic acid. Suitable ethylene copolymers have from 0.1% by weight to 35% by weight of unsaturated carboxylic acid, based on the total copolymer. Preferably, the copolymers have from 1% by weight to 20% by weight of the unsaturated carboxylic acid on the same basis.

The method by which the copolymers are prepared is not critical and ethylene/unsaturated acid copolymers produced by a variety of methods are usefully employed when polyketone blends are used in the flame spraying process. A number of ethylene/acrylic acid and ethylene/methacrylic acid copolymers are commercially available. A general discussion of the production of ethylene/unsaturated carboxylic acid copolymers is found in US-3,520,861 and US-4,351,931.

Blends containing up to about 80% by weight, based on total blend, of the ethylene/unsaturated carboxylic acid copolymer may be prepared, however, blends of up to 35% by weight may be flame-sprayed in a satisfactory manner. Blends containing from 0.1% to 10% by weight of ethylene/unsaturated carboxylic acid copolymer, based on total blend, are preferred and particularly preferred, when blends are to be employed, are polyketone blends containing from 3% to 7% by weight, on the same basis, of the ethylene/unsaturated carboxylic acid copolymer.

The method of forming a blend to be used in the process of the invention, when blends are employed, is not material so long as a uniform blend of the components is produced without undue degradation of the components or the resulting blend. In one embodiment the polyketone polymer and the ethylene/unsaturated carboxylic acid copolymer are co-extruded to produce the blend as an extrudate. In another embodiment, the components are dry blended as powders or blended in a mixing device which exhibits high shear. The polyketone blend with ethylene/unsaturated carboxylic acid copolymer is a non-miscible blend wherein the ethylene/unsaturated acid copolymer exists as a discrete phase in the polyketone matrix. Satisfac-

tory phase size for use in the invention is in the order of 0.2 to 1.5 μm , preferably from 0.5 to 1.0 μm . The blend is, of course, not homogeneous but good results are obtained in the process of the invention when the blend is a uniform mixture of the dispersed ethylene/unsaturated carboxylic acid copolymer in the continuous polyketone phase.

The blends used in the process of the invention may optionally contain other conventional additives such as antioxidants, stabilizers and fire retardant materials and other additives designed to improve the processability of the polymers or improve the properties of the resulting blend. Such additives are added by conventional methods prior to, together with or subsequent to the blending of the component polymers.

A suitable device for flame spraying the present thermoplastic polymeric materials is an apparatus wherein the polymeric material, a fuel and oxygen-containing gas are introduced into a combustion chamber wherein the fuel and oxygen-containing gas mixture ignites, thereby giving off heat which serves to substantially melt the polymeric material. The molten polymeric material is thereafter propelled from the combustion chamber by a source of propelling gas onto the surface of the object to be coated. A modification of the process, also often termed flame spraying, although not directly involving a flame, employs the use of a heated wire or filament to melt the polymer to be sprayed. The use of a flame produced by combustion of a fuel in air is generally preferred.

Illustrative fuels are generally low-molecular weight hydrocarbons which ignite easily and are normally gaseous at ambient conditions. Examples of suitable fuels include propane, propylene, ethylene and acetylene. Propane is convenient. As the oxygen-containing gas employed to cause combustion of the fuel, a variety of mixtures of oxygen and other non-combustible gases are usefully employed. Air is preferred. A variety of gaseous materials is useful as the propelling gas including nitrogen, argon and helium. Largely for convenience and economy, the use of air as the propelling gas as well as the combustion gas is preferred. Examples of such flame spraying processes and apparatus therefor are known in the art. A particularly useful process and equipment for use in the process is described in US-4,632,309. Other related processes are illustrated by US-4,604,306, US-3,723,165 and US-3,440,079.

The state of division of the polymeric material powder as well as the viscosity of the polyketone polymer, is important in obtaining good coatings on the target object. The polymeric material to be flame sprayed should be of a size from 0.15 to 0.85 mm (20-100 mesh), preferably from 0.18 to 0.30 mm (50-80 mesh). The limiting viscosity num-

ber of the polyketone polymer (LVN, measured at 60°C in m-cresol) should be from 0.5 to 1.8 and preferably is below 1.4.

The object to be coated is a solid object for which a tough, wear and corrosion resistant coating is desired and objects of metal, glass, ceramic, plastic or other material are coated by the present process. More frequently, the process is employed to provide a coating of polyketone or blend thereof on metal objects. The process of the invention may be used in conjunction with other polymeric coatings wherein the object to be coated has a base coat of a first polymeric composition, such as a polyolefin, and a subsequent top coat of polyketone or polyketone blend. Alternatively, the coating comprising polyketone may be used to provide a base coat suitable for subsequent top coating with a second composition. The process is particularly suitable for coating both internal and external automotive parts such as drive shafts and suspension springs and for coating storage tanks, food processing equipment and industrial pipe.

The invention is further illustrated by the following Examples.

Example I

A. A linear alternating copolymer of carbon monoxide and ethylene was produced by contacting the carbon monoxide and ethylene in the presence of a catalyst composition formed from palladium acetate, the anion of trifluoroacetic acid and 1,3-bis[di(2-methoxyphenyl)phosphino]propane. The copolymer had a melting point of 250°C and a LVN (measured at 60°C in m-cresol) of 1.3.

Three linear alternating terpolymers of carbon monoxide, ethylene and propylene were separately produced in the presence of catalyst compositions formed from palladium acetate, the anion of trifluoroacetic acid and 1,3-bis[di(2-methoxyphenyl)phosphino]propane. The terpolymers each had a melting point of 220°C and LVN (measured at 60°C in m-cresol) of 1.2, 1.6 and 2.2, respectively.

B. The terpolymers of paragraph A were separately employed in a flame spraying process to coat metal plates of aluminium and steel approximately 7.5 by 17.5 cm with a thickness of 1.6 mm. The terpolymers were used as powders of roughly 50 to 80 mesh and the powders were dried prior to use.

The metal plates were flame dried and then coated by flame spraying for approximately four minutes each until a film coating thickness of 0.76 mm was achieved on each plate. The bond of the polymer coating to the metal plates was tested in ASTM Crosshatch Adhesion Test #D3359-78. In

this standardized test procedure, a six-blade cutting apparatus is first used to score and crosshatch the polymer coating down to the metal surface. A special ASTM adhesive tape is applied to the top surface of the coating and subsequently pulled from the surface at an acute angle to test the adhesion of the coating to the metal substrate. The adhesion of the coating is rated from 1 to 5 according to the number of crosshatch squares that are removed by the tape, 5 being the highest rating. The coatings prepared with the terpolymers of Example I were all rated 5.

Example II

The copolymer of Example I, paragraph A was blended separately with 30% by weight, based on total blend, of two commercially available ethylene-acrylic acid copolymers. The first one was a copolymer of ethylene and 9.5% by weight based on copolymer of acrylic acid. The second one was a copolymer of ethylene and 20% by weight based on copolymer of acrylic acid. The blend of the latter copolymer also contained carbon black as a colourizing agent.

The blends were employed in a flame spraying process as in Example IB to coat aluminium and steel plates. The coatings were tested after they were prepared in ASTM Crosshatch Adhesion Test #D3359-78, as in Example 1B. All of the coatings were rated 5.

Example III

The terpolymer of Example 1A having an LVN of 2.2 was blended separately with 20, 40, 60 and 80% by weight, based on total blend, of the first ethylene-acrylic acid copolymer of Example II. The blend was employed in a flame spraying process to coat metal plates as in Example IB and the coatings were tested in the ASTM Crosshatch Adhesion Test described before. The coatings were all rated 5.


The coated plates were tested for Gardner Impact strength with a 900 g weight and all of the coatings were rated at over 90 kg.cm. In several cases, the metal plates cracked during testing, but not the polymeric coatings.

Claims

1. Process for coating a solid object with a polymeric material by flame spraying characterized in that a powder having a particle size of 0.15-0.85 mm comprising a linear alternating polymer of car-

bon monoxide and at least one ethylenically unsaturated compound, which linear alternating polymer has a limiting viscosity number of 0.5-1.8 (as measured at 60° C in m-cresol), is heated to substantially melt the powder, and is thereafter propelled onto the surface of the solid object.

2. A process as claimed in claim 1, wherein the linear alternating polymer is represented by the formula



wherein B is the moiety of an ethylenically unsaturated hydrocarbon of at least 3 carbon atoms and the ratio of y:x is no more than 0.5.

3. A process as claimed in claim 1 or 2, wherein the polymeric material comprises in addition up to 35% by weight (based on the total) of a copolymer of ethylene and from 0.1% to 35% by weight (based on total copolymer) of an alpha,beta-ethylenically unsaturated carboxylic acid.

4. A process as claimed in claim 3, wherein the copolymer is a copolymer of ethylene and from 1% to 20% by weight (based on total copolymer) of an alpha,beta-ethylenically unsaturated carboxylic acid of up to 4 carbon atoms inclusive.

5. A process as claimed in claim 4, wherein the copolymer is a copolymer of ethylene and acrylic acid.

6. A process as claimed in any of claims 1-5, wherein the quantity of copolymer is from 3 to 7% by weight based on total blend.

7. A process as claimed in any of claims 2-6, wherein y = 0.

8. A process as claimed in any of claims 2-6, wherein B is a moiety of propylene and the ratio of y:x is from 0.01 to 0.1.

9. A coated object whenever prepared by a process as claimed in any of claims 1-8.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 339 742 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89201064.6

(51) Int. Cl.⁵: C09D 3/48, C23C 4/04,
C08G 67/02, C08J 5/12

(22) Date of filing: 25.04.89

(30) Priority: 25.04.88 US 185577

(43) Date of publication of application:
02.11.89 Bulletin 89/44

(84) Designated Contracting States:
BE CH DE ES FR GB IT LI NL SE

(88) Date of deferred publication of the search report:
24.07.91 Bulletin 91/30

(71) Applicant: SHELL INTERNATIONALE
RESEARCH MAATSCHAPPIJ B.V.
Carel van Bylandtlaan 30
NL-2596 HR Den Haag(NL)

(72) Inventor: George, Eric Richard
13703 Overbrook Lane
Houston Texas 77077(US)

(74) Representative: Aalbers, Onno et al
P.O. Box 302
NL-2501 CH The Hague(NL)

(54) Process for coating a solid object with a polymeric material.

(57) A coated object is produced by flame spraying the object with a substantially molten polymeric material which comprises a linear alternating polymer of ethylene and at least one ethylenically unsaturated compound, optionally blended with a copolymer of ethylene and alpha,beta-ethylenically unsaturated carboxylic acid.

EP 0 339 742 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 20 1064

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	US-A-4 046 728 (C.M. HARMUTH) -----		C 09 D 3/48 C 23 C 4/04 C 08 G 67/02 C 08 J 5/12
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 09 D C 08 G B 05 D C 08 L
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of search 01 March 91	Examiner KLIER E.K.
<div><div><p>CATEGORY OF CITED DOCUMENTS</p><p>X: particularly relevant if taken alone</p><p>Y: particularly relevant if combined with another document of the same category</p><p>A: technological background</p><p>O: non-written disclosure</p><p>P: intermediate document</p><p>T: theory or principle underlying the invention</p></div><div><p>E: earlier patent document, but published on, or after the filing date</p><p>D: document cited in the application</p><p>L: document cited for other reasons</p><p>&: member of the same patent family, corresponding document</p></div></div>			

